

Color is secondary, but should be somewhat uniform with ordinary standards of military or security units. Military oX stock oil has a unique feature regarding the shade adjustment of the oil to obtain a preference or slight correction for certain stockwoods or light areas, etc. within all stockwoods.

#### TO ADJUST SHADE OF MILITARY oX STOCK OIL:

a. FOR REDDEST TONES: Shake the can, inverted, for at least three minutes in a room temperature (65 to 85 degrees f.) setting. Open immediately and pour off 1 to 2 oz. oil into your finishing jar. Stir every time you dip to apply to ensure the red stays in the mix.

b. FOR LESS RED, MORE BROWN - WALNUT TONES: Shake the can the same way and duration. Pour off enough to do the job at hand into one small jar, let settle to your preference, (the red falls out much more quickly than any other pigment from Military oX stock oil, leaving browner oil for commercial rifles and shotguns where appropriate). Pour off into a second jar leaving the red pigments on the bottom of jar 1. From the original can, pour a small amount of oil into jar 1 and stir the red back into the mix, then pour back into original can and seal tightly for long shelf life. Proceed with application from jar 2.

4. PLACE WOOD STOCK PIECES ON PENCILS OR DOWELS TO ELEVATE ABOVE A CARDBOARD COVERING YOUR WORK SURFACE, turning stock pieces often to rewet areas that appear to dry out faster. Further sanding is not needed at this time; just pat it on with a small corner of rag or sponge. REFRAIN FROM SANDING THOSE AREAS SENSITIVE TO LOCK-UP. DO NOT SAND IN THE RECEIVER WELL. SOAK IT AND ALL WOOD AREAS WELL, THOUGH, AND WIPE ALL SANDED AND SOAKED AREAS TIGHT SIMULTANEOUSLY AT THE END OF THE SOAKING PERIOD. (Which should be around 1 hour at room temperature for maximum effect)

Note: (def.) "Wiping tight": Removing all the oil and residue from the stock wood after soaking with stock oil. Use clean, dry paper towels. Don't rub exceedingly hard with paper towels. It has a burnishing effect and creates shine. Rub with moderate pressure until a clean towel picks up no more color.

5. AFTER WIPING TIGHT, RUB THE SURFACE WITH THE BARE HEEL AND PALM OF YOUR HAND UNTIL IT GETS HOT ENOUGH YOU NEED TO MOVE YOUR HAND.

a. Use moderately firm pressure when hand-rubbing, and rub all the wood warm with this technique.

6. SET ASIDE ONE HOUR, THEN WIPE TIGHT AGAIN WITH CLEAN PAPER TOWEL.

7. PROPERLY LUBRICATE YOUR STEEL AND REASSEMBLE THE RIFLE. The soak takes about three days to cure completely, but it will be dry to the touch in a couple of hours from the start and the firearm can be reassembled and used immediately.

Note: Re-apply Military oX lightly the next day without disassembling. Let soak 15 minutes and wipe tight. Hand-rub wood again. Towel again. Wipe any oil on metal off with the corner of a damp thinner rag. I recommend premium, odorless, mineral spirits for all clean up.

NEVER THIN FAIRTRIMMER'S MILITARY oX STOCK OIL. Keep wood to be treated clean and dry for application. DO NOT SOAK WOOD WITH SOLVENT IMMEDIATELY PREVIOUS TO TREATING WITH FAIRTRIMMER'S MILITARY oX STOCK OIL. IF PRE-STAINING IS NEEDED, USE COMPATIBLE STAIN AND LET DRY COMPLETELY PRIOR TO APPLICATION OF MILITARY oX.

8. SCRATCHES, SCUFFS, ETC., CAN BE REPAIRED BY RESANDING AREA LIGHTLY W/180 TO OPEN UP, APPLYING oX OIL WITH 320, SOAKING 20 OR 30 MINUTES, WIPING TIGHT AND HAND-RUBBING AS BEFORE. Unless gouged deeply, the repair will normally blend seamlessly.

NOTE: Use the same steps, same sequence to refurbish the stock anytime you please.